

	Metodo di prova Testing method Méthode d'essai Prüfmethode Método de prueba Метод испытаний	Unità di misura Measurement unit Unité de mesure Maßeinheit Unidad de medida Единица измерения	Valori Tipici Medi Average Typical Values Valeurs Moyennes Typiques Typische Durchschnittswerte Valores Típicos Medios Средние значения	Valori limite previsti Established limits Valeurs limites Prévises Vorgeschene Grenzwerte Valores límite previstos Прогнозируемые предельные значения	Norma di riferimento Reference standard Norme de référence Bezugsnorm Norma de referencia Ссылка на норму	
	Absorbimento d'acqua in % Water absorption in % Absorption d'eau en % Wasserabsorption in % Absorção de água em % Водопоглощение %	ISO 10545-3	%	≤ 0,5	Valore massimo singolo 0,6% Maximum single value 0,6% Valeur unique maximale 0,6% Höchstiger Einzelwert 0,6% Valor único máximo 0,6% Максимальное значение 0,6%	UNI EN 14411-G
	Dimensioni Dimensions Dimensions Abmessungen Dimensiones Размеры	ISO 10545-2			N ≥ 15 cm	
	Lunghezza e Larghezza Length and width Longueur et largeur Länge und Breite Longitud y anchura Длина и ширина				± 2 mm ± 0,5%	
	Spessore Thickness Épaisseur Stärke Espesor Толщина				± 0,5 mm ± 5%	
	Rettilineità degli spigoli Edge straightness Rectitude des arêtes Geradigkeit der Kanten Rectitud de los cantos Прямизна углов		mm %		± 1,5 mm ± 0,5%	
	Ortogonalità Orthogonality Orthogonalité Rechtwinkligkeit Ortogonalidad Ортогональность				± 2 mm ± 0,5%	
	Pianità Flatness Planéité Ebenförmigkeit Planidad Плоскостность				± 2 mm ± 0,5%	
	Aspetto Appearance Aspect Aussehen Aspecto Внешний вид			100%	≥ 95%	
	Resistenza alla flessione Bending strength Résistance à la flexion Biegefestigkeit Resistencia a la flexión Стойкость изгиба	ISO 10545-4				
	Modulo di rottura Modulus of rupture Module de rupture Bruchmodul Módulo de rotura Прочность на разрыв		N/mm ²	≥ 35	Ra35 Valore singolo minimo 32 Minimum single value 32 Valeur unique minimale 32 Geringer Einzelwert 32 Valor único mínimo 32 Минимум одно значение не менее 32	
	Sforzo di rottura Breaking strenght Force de rupture Bruchkraft Esfuerzo de rotura Прочность на разрыв		N	≥ 1300	≥ 1300	
	Resistenza all'abrasione profonda Resistance deep abrasion Résistance à l'abrasion profonde Tiefenabriebfestigkeit Resistencia a la abrasión profunda Устойчивость к глубокой абразии	ISO 10545-6	mm ³	120-150	≤ 175	
	Resistenza al gelo Frost resistance Résistance au gel Frostbeständigkeit Resistencia a la helada Морозостойкость	ISO 10545-12		Resiste Resistant Résistant Resistente Creskeli	In accordo alla norma EN ISO 10545-1 In accordance with the en iso 10545-1 standard Conformément à la norme d'EN ISO 10545-1 Conform mit der Norm DIN ISO 10545-1 De conformidad con la norma EN ISO 10545-1 В соответствии со стандартом EN ISO 10545-1	

	Metodo di prova Testing method Méthode d'essai Prüfmethode Método de prueba Метод испытаний	Unità di misura Measurement unit Unité de mesure Maßeinheit Unidad de medida Единица измерения	Valori Tipici Medi Average Typical Values Valeurs Moyennes Typiques Typische Durchschnittswerte Valores Típicos Medios Средние значения	Valori limite previsti Established limits Valeurs limites Prévises Vorgeschlene Grenzwerte Valores límite previstos Прогнозируемые предельные значения	Norma di riferimento Reference standard Norme de référence Bezugsnorm Norma de referencia Ссылка на норму	
	Resistenza agli sbalzi termici Thermal shock resistance Résistance aux écart de température Widerstandsfähigkeit gegen Temperaturschwankungen Resistencia al choque térmico Устойчивость к температурным скачкам	ISO 10545-9		Resistente Resistant Résistant Beständig Resistente Стойкий	In accordo alla norma EN ISO 10545-1 In accordance with the en iso 10545-1 standard Conformément à la norme d'EN ISO 10545-1 Conform mit der Norm DIN ISO 10545-1 De conformidad con la norma EN ISO 10545-1 В соответствии со стандартом EN ISO 10545-1	
	Coefficiente di dilatazione termica lineare Linear thermal expansion coefficient Coefficient de dilatation thermique linéique Linear Wärmeausdehnungskoeffizient Coeficiente de dilatación térmica lineal Коэффициент линейного температурного расширения	ISO 10545-8	MK ⁻¹	≤ 9	Valore dichiarato Value declared Valeur déclarée Erklärter Wert Valor declarado Значение заявлено	
	Resistenza alle macchie Stain resistance Résistance aux taches Fleckenbeständigkeit Resistencia a las manchas Стойкость к пятнам	ISO 10545-14		Classe 5 Class 5 Classe 5 Kategorie 5 Klasse 5	Classe 3 minimo Class 3 minimum Classe 3 minimum Mind. Klasse 3 Categoría 3 mínimo Minimale Klasse 3	
	Resistenza ai prodotti chimici di uso domestico e sali per piscine Resistance to chemicals for household use and swimming pool salts Résistance aux produits chimiques d'usage domestique et sels pour piscine Beständigkeit gegen Haushaltschemikalien und Zusätze für Schwimmbäder Resistencia a los productos químicos para uso doméstico y sales para piscinas Устойчивость к бытовым химическим препаратам и солям для бассейнов	ISO 10545-13		GA	GB Minimo GB Minimum GB Minimum GB Minimum GB Minimo GB mindestens	UNI EN 14411-G
	Resistenza agli acidi ed alle basi Resistance to acids and bases Résistance aux acides et aux bases Säure- und Laugenbeständigkeit Resistencia a los ácidos y a las bases Стойкость к кислотам и щелочам			da GLA a GLB / da GHA a GHB non GLA to GLB / from GHA to GHB de GLA à GLB / de GHA à GHB von GLA bis GLB / von GHA bis GHB de GLA a GLB / de GHA a GHB o/L GLA a/L GLB / o/L GHA a/L GHB	Valore dichiarato Value declared Valeur déclarée Erklärter Wert Valor declarado Значение заявлено	
	Resistenza dei colori alla luce Color resistance to light exposure Résistance des couleurs à la lumière Lichtechtheit der Farben Resistencia de los colores a la exposición de la luz Стойкость окраски к свету	DIN 51094		Conforme Complies with the standards Conforme aux normes Anforderungen erfüllt Conforme con las normas Conformity met	No deve presentarsi alcun cambiamento di colore. No change must show noticeable color modification. Aucun changement de couleur n'est autorisé. Keine Veränderung der Farbtöne ist zulässig. Ninguna modificación de coloración es permitida. Не должно наблюдаться изменение окраски.	
	Resistenza allo scivolamento Slip resistance Résistance au glissement Rutschhemmung Resistencia al deslizamiento Comportamiento antideslizante Ardea, Molepa, Serina, Piantina, Luarna, Piana Glacé, Quorra, Luarna Stail, Garzhe Stail, Rera Blue Stail, Ravenna Bora, Serina Rip, Molepa Bora	RAMP METHOD		R9	da R9 a R13 from R9 to R13 de R9 à R13 von R9 bis R13 de R9 a R13 or R9 pp R13	DIN 51130 BGR 181 ¹
	Resistenza allo scivolamento Slip resistance Résistance au glissement Rutschhemmung Resistencia al deslizamiento Comportamiento antideslizante	PENDULUM		Classe 1 Class 1 Classe 1 Kategorie 1 Categoría 1 Klasse 1		EN 12633 BCE N°74 DEL 26/3/05

1 Pavimentazioni di ambienti lavorativi e zone operative con superfici antiscivolo.
Flooring of work environments and operating areas with slippery surfaces.
Sols de locaux industriels et de zones de travail à surfaces dérapantes.
Bodenbeläge für Arbeitsräume und Arbeitsbereiche mit Rutschgefahr.
Pavimentaciones de zonas de trabajo y operativas con superficies resbaladizas.
Полы в рабочих помещениях и рабочих зонах со скользкими поверхностями.

N Dimensione nominale (cm)
N Nominal dimension (cm)
N Dimension nominale (cm)
N Nominal (cm)
N Dimension nominal (cm)
N Номинальный размер (см)